

PRODUCT INFORMATION

**634** GREASE

### Heat Sink Compound

#### Applications

ASV 634 compound is used as a heat transfer media in the electrical and electronic industry for facilitating heat dissipation by filling voids and gaps between power components and heat sinks. Useful for the following applications:

- Thermocouple Wells
- Thermometer Wells
- Mounting Power Diodes & Transistors
- Shock & Heat Dissipation in Transistors
- Mounting Semi-Conductor Devices
- Heat Transfer Medium on Ballasts
- Thermal Joints
- Sensors
- Thermistors

#### **Benefits**

- Wide service temperature range from -54°C to +200°C
- Low evaporation at high temperatures
- Very low bleed characteristics
- High thermal conductivity
- Exceptional oxidation stability
- Non melting, non-hardening and non-drying

#### **Directions for Use**

Use as supplied. Never dilute or mix with other oil or grease. Apply in small quantities on clean surfaces that are absolutely free from dust, foreign particles or contaminants. Squeeze out extra compound by pressing both the surfaces after application and wipe clean to prevent accumulation of dirt & dust.





PRODUCT INFORMATION

# ASV®

## **634** Grease

| TECHNICAL PROPERTY                      |                      |                   |             |
|---|----------------------|-------------------|-------------|
| Parameter                               | Value                | Unit              | Standard    |
|   |                      |                   |             |
| Appearance                              | Smooth grease        |                   |             |
| Base oil                                | Silicone             |                   |             |
| Thickener                               | Inorganic            |                   |             |
| Color <sup>1</sup>                      | White                |                   |             |
| Penetration, worked, 60 strokes         | 275                  | mm/10             | ASTM D 217  |
| Density, @ 25°C                         | 2                    | g/cm <sup>3</sup> |             |
| Drop point                              | None                 | °C                | ASTM D 566  |
| Service temperatures                    | -54°C to +200°C      | °C                |             |
| Bleed, 24h, 200°C                       | 0.05                 | % by wt.          |             |
| Evaporation, 24h, 200°C                 | 0.5                  | % by wt.          |             |
| Thermal conductivity, K Factor          | 0.0015               | cal/sec-cm-°C     |             |
| Dielectric strength (50 mils thickness) | 210                  | volts/mil         | ASTM D 149  |
| Arc resistance                          | 165                  | seconds           | ASTMD 495   |
| Dielectric constant                     | _                    |                   | ASTM D 150  |
| - 100 Hz<br>- 100 kHz                   | 5<br>5               |                   |             |
| Dissipation factor                      | 0                    |                   |             |
| - 100 Hz                                | 0.01                 |                   | ASTIVED 150 |
| - 100 kHz                               | 0.02                 |                   |             |
| Volume resistivity                      | 2 x 10 <sup>15</sup> | ohm/cm            | ASTM D 1169 |

#### General

Use in well ventilated areas. Avoid continuous breathing of vapor and spray mist. In closed areas or areas with poor ventilation, use respiratory protection. For complete details on safety, short and long term exposure, refer to this product's safety data sheet (SDS).

#### Disposal

All used and unused product should be disposed of in accordance with state regulations.

#### Handling

Read instructions on the container label of the product before use. The product safety data sheet (SDS) contains the relevant information regarding personal protective equipment, safe use, physical and health hazards. Safety data sheet is available from ASV or your local ASV distributor.

Manufactured by ASV Multichemie Private Limited W 46, TTC Industrial Area, MIDC Rabale, Navi Mumbai 400 701 INDIA Contact: +91 22 2764 2516 Email: info@asvmultichemie.com

#### **Available Packaging**

1 kg

#### Shelf Life

36 months from date of manufacture in sealed condition.

#### **Limited Warranty**

The information and data contained in this sheet is accurate to the best of our knowledge or is obtained from sources, tests or experiences believed by us to be reliable and accurate. User is responsible for determining whether recommended ASV product is fit for a particular purpose. All products should be tested for suitability on a particular application prior to actual use. We make no representations of any kind. Data offered without warranty. Product manufactured is for industrial use only.

#### WWW.ASVMULTICHEMIE.COM

ASV<sup>®</sup> MOLYSULF<sup>®</sup> PENETROIL<sup>®</sup> SHINY GALVA<sup>®</sup> VALV-KOTE<sup>®</sup> BRIGHT ZINK<sup>®</sup> SPEZET<sup>®</sup> MOLYCHEM<sup>®</sup> TRIBOSULF<sup>®</sup> are Registered Trademarks of ASV MULTICHEMIE PRIVATE LIMITED, INDIA. ALL DATA OFFERED WITHOUT LIABILITY OR WARRANTY.