

## LL 102

## GREASE

### Heavy duty, extreme pressure grease containing MoS<sub>2</sub> solid lubricant for lubrication of sliding metal surfaces under high loads

#### Applications

- Use successfully for roller bearing, all types of anti-friction bearings, plain bearings, roller guides, threaded spindles, splined shafts, taper bearings, needle roller bearings, sliding and mating surfaces under vibratory or reciprocating motions, journal bearings, couplings.
- For heavy duty and long-term lubrication to bearings and equipment of heavy engineering machinery, textile processing machines, compressors, exhaust fans, overhead cranes, mining and construction equipment, rolling mills.
- For long lasting lubrication of cams, shafts, spring, joints, steel cables; for lubrication of small gear mechanisms exposed to severe impact loads and slow operating speeds.

#### Benefits

- Extremely wide service temperature range of -25°C to +110°C (short peaks to +130°C)
- Excellent resistance to water and water washout
- Extends re-lubrication intervals and cuts down lubricant consumption
- Combination of EP additives increase the load bearing capacity
- Offers good surface protection and corrosion inhibiting properties
- Very good performance under moderate to high loads and medium speeds under reciprocating motions
- Makes sliding smoother and reduces operational noise
- Increases wear life of the equipment & out performs conventional lubricants
- Good resistance to oxidation and corrosion

#### Directions for Use

Use as supplied. Never dilute or mix with oil or grease. Apply on all clean sliding surfaces by normal greasing methods i.e. by brush, grease gun or dispense via centralized lubrication systems. Replace cover after use.

## LL 102

## GREASE

| TECHNICAL PROPERTY                         |  |                    |                 |
|--|--|--------------------|-----------------|
| Parameter                                  | Value  | Unit               | Standard        |
| Type                                       | Grease with EP/AW additives and solid lubricants |                    |                 |
| Appearance                                 | Smooth grease                                    |                    |                 |
| Base oil                                   | Mineral  |                    |                 |
| Base oil viscosity, @ 40°C                 | 260  | mm <sup>2</sup> /s | DIN 51 562      |
| Thickener                                  | Lithium  |                    |                 |
| Color                                      | Black  |                    |                 |
| Penetration, worked                        | 265-295  | mm/10              | ASTM D 217      |
| NLGI Consistency                           | 2  | Class              | DIN 51 818      |
| Density, @ 25°C                            | 0.85- 0.95                                       | g/cm <sup>3</sup>  |                 |
| Drop point                                 | + 185  | °C                 | ASTM D 566      |
| Service temperatures                       | -25 to +110<br>(+ 130 for short periods)         | °C                 |                 |
| Four ball wear test, weld load             | 3700   | N                  | DIN 51 350 pt.4 |
| Four ball wear test, wear scar, 800N       | 1.1  | mm                 | DIN 51 350 pt.5 |
| DN value                                   | 250,000  | mm/min             |                 |
| Oxidation resistance, pressure drop        | 0.3  | bar                | DIN 51 808      |
| Oil separation, standard test, 168 h, 40°C | < 2  | %                  | DIN 51 817      |

### General

Use in well ventilated areas. Avoid continuous breathing of vapor and spray mist. In closed areas or areas with poor ventilation, use respiratory protection. For complete details on safety, short and long term exposure, refer to this product's safety data sheet (SDS).

### Disposal

All used and unused product should be disposed of in accordance with state regulations.

### Handling

Read instructions on the container label of the product before use. The product safety data sheet (SDS) contains the relevant information regarding personal protective equipment, safe use, physical and health hazards. Safety data sheet is available from ASV or your local ASV distributor.

Manufactured by  
ASV Multichemie Private Limited  
W 46, TTC Industrial Area, MIDC Rabale,  
Navi Mumbai 400 701 INDIA  
Contact: +91 22 2764 2516  
Email: info@asvmultichemie.com

### Available Packaging

1 kg, 5 kg, 20 kg, 180 kg

### Shelf Life

36 months from date of manufacture in sealed condition.

### Limited Warranty

The information and data contained in this sheet is accurate to the best of our knowledge or is obtained from sources, tests or experiences believed by us to be reliable and accurate. User is responsible for determining whether recommended ASV product is fit for a particular purpose. All products should be tested for suitability on a particular application prior to actual use. We make no representations of any kind. Data offered without warranty. Product manufactured is for industrial use only.

**WWW.ASVMULTICHEMIE.COM**

ASV® MOLYSULF® PENETROIL® SHINY GALVA® VALV-KOTE® BRIGHT ZINK® SPEZET® MOLYCHEM® TRIBOSULF® are Registered Trademarks of ASV MULTICHEMIE PRIVATE LIMITED, INDIA.  
ALL DATA OFFERED WITHOUT LIABILITY OR WARRANTY.